

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-109395

(43)Date of publication of application : 18.04.2000

(51)Int.Cl.

C30B 29/06
C30B 33/02
H01L 21/02
H01L 21/208
H01L 21/324

(21)Application number : 10-292995

(71)Applicant : TOSHIBA CERAMICS CO LTD

(22)Date of filing : 30.09.1998

(72)Inventor : HIRANO YUMIKO

ARAKI KOJI

SAKUMA MASAKI

KOBAYASHI AKIHIKO

KUBOTA OSAMU

MATSUYAMA SHUNICHIRO

KUROKAWA MASAHICO

OSANAI JUNICHI

(54) SILICON SINGLE CRYSTAL WAFER AND ITS PRODUCTION

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a wafer in which substantially no void having size equal to a prescribed value or larger exists and which can be treated in a treatment stage such as heat treatment stage to obtain a treated product wafer having drastically reduced density of voids existing in the surface as compared with a conventional similar treated product wafer, and from which a product excellent in oxide film dielectric strength can be manufactured, and also to provide the production process of the wafer.

SOLUTION: In this wafer which is produced from a single crystal pulled up by a Czochralski method, the size distribution of voids that appear in the surface of the wafer meets the following conditions: the number of voids having 0.1-0.15 μm size is $\geq 85\%$ of the total void number (wherein the term 'total void number' is defined as the total number of voids that exist in the wafer surface and have $\geq 0.1 \mu\text{m}$ size); and substantially no void having $\geq 0.20 \mu\text{m}$ size exists in the wafer surface.

LEGAL STATUS

[Date of request for examination] 02.08.2001

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3611236

[Date of registration] 29.10.2004

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]